

ZINC PHOSPHATE PRIMER

Surface Preparation	<p>All surfaces must be firm, dry and clean, free from oil, grease or any other contaminants. Degrease with AQUASOLV DEGREASER (GR 1) and rinse thoroughly with fresh water. Allow to dry.</p> <p>MILD STEEL:</p> <ul style="list-style-type: none"> • Abrasive blast clean to Grade Sa 2 ½ of ISO 8501-1:1988 or prepare substrate mechanically so that the surface has a pronounced metallic sheen (Grade St3 of the same standard). • Mechanical cleaning is not as effective and results in a shorter maintenance-free life.
Application	<ul style="list-style-type: none"> • Thin as recommended. • Apply using airless or conventional spray to achieve the required DFT. • Do not apply excessively thick coats. • Overcoatable with alkyd topcoats.
Caution	<ul style="list-style-type: none"> • Ensure product is mixed well and completely homogenous prior to use. • Before overcoating ZINC PHOSPHATE PRIMER ensure that the primer surface is thoroughly clean- use POLYCELL SUGAR SOAP SOLUTION and abrasive pads if necessary and rinse well with water. • Not recommended for water immersion conditions
Safety Precautions	<ul style="list-style-type: none"> • Always keep paint out of reach of children. • Ensure good ventilation during application and drying. • If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. Harmful if swallowed. Seek medical attention and do not induce vomiting. • Do not smoke while painting. • Flammable. Store in a cool dry place away from heat and sparks. • Refer to Material Safety Data Sheet for complete information.

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B.: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

BARLOWORLD PLASCON SOUTH AFRICA (PTY) LIMITED

CAPE TOWN:

P O Box 42
Eppindust 7475
Tel: (021) 534-6151
Fax: (021) 534-3791

DURBAN:

Private Bag X16
Mobeni 4060
Tel: (031) 451-3200
Fax: (031) 451-3411

MOGALE CITY

(KRUGERSDORP):
Private Bag X4010
Kenmare 1745
Tel: (011) 951-4500
Fax: (011) 955-4136

PORT ELIZABETH:

P O Box 1594
Port Elizabeth 6000
Tel: (041) 401-1400
Fax: (041) 434-606