



PROFESSIONAL VINOPLAST TEXTURED ACRYLIC

TECHNICAL DATA SHEET NO.:
DATE:

L-34-H
OCTOBER 2004

PRODUCT CODE: PTX 1000

THIS SUPERSEDES ALL PREVIOUS PUBLICATIONS

| | | | |
|------------------------------|---|--|------------------------------|
| Product Description | Heavy duty wall cladding with a variable texture for use on cement plaster and other suitable surfaces. It is an extremely tough, durable coating –with good mechanical properties. | | |
| Intended Uses | <ul style="list-style-type: none"> • Ideal for interior surfaces such as passages, staircases, dados, etc. • VINOPLAST, with a smooth velvet finish, is the ideal material for roller or spatter application and by varying the colour of the roller base coat with contrasting spatter colour and spatter patterns, one can achieve a multitude of durable, aesthetically pleasing finishes. • A gloss finish is obtained with the application of TEXTURE PAINT GLAZE COAT (CV 82) resulting in a completely washable surface that does not gloss up. | | |
| Product Information | Appearance | Satin sheen texture | |
| | Colour | White | |
| | Solids | Approx. 67 % by mass; 54 % by volume | |
| | Recommended DFT | Max.: 250 -500 µm | |
| | Theoretical spreading rate | 2 m ² /ℓ 250 µm DFT | |
| | Practical spreading rate | The actual spreading rate will normally vary depending on surface conditions and the texture required and must be determined by the user. | |
| | Viscosity at 23 °C | Thixotropic paste | |
| | S G at 23°C | 1,44 kg / ℓ (typical) | |
| | Flash point | > 65°C | |
| Application Details | Mixing | Stir thoroughly with a flat paddle until homogeneous. | |
| | Method | Brush, medium pile synthetic roller, "honeycomb" type texture roller and spray (spattering). | |
| | Thinner | Basecoat - for roller application - VINOPLAST REDUCER (ABV 901) . Spattercoat - Water | |
| | Thinning | Basecoat - approx. 250 ml per 25 l VINOPLAST depending on required texture. Spatter coat - minimum thinning required for spotting. | |
| | Cleaning | Water - do not allow product to dry on equipment. | |
| | Substrate | Well prepared, primed and sealed surfaces. | |
| | Application Environment | Surface Temperature | Ambient Temperature |
| | | Min.: 5 °C | Min.: 5 °C |
| | | or 2 °C min. above dew point | |
| | | Max.: 40 °C | Max.: 40 °C |
| | | | Relative Humidity |
| | | | - |
| | | | Max.: 85 % |
| | Drying time | Touch dry | 2 h at 23 °C |
| | | Recoating | 24 h at 23 °C |
| | | Dry to handle | 24 h at 23 °C |
| | | Hard dry | 48 h at 23 °C |
| | | | Hardness improves on ageing. |
| Storage and Packaging | Store away from direct sun, heat and severe cold. Packaging: 20ℓ. | | |
| Transportation | This product is non-classifiable in accordance with Transportation and Classification of Dangerous Goods Act (1996) | | |

PROFESSIONAL VINOPLAST TEXTURED ACRYLIC

| | |
|----------------------------|---|
| Surface Preparation | <ul style="list-style-type: none"> • Ensure that surfaces are dry, firm, free from dust, dirt, grease, oil and other contaminants. • For maximum durability a hard cement plaster is recommended such as a 4: 1 mixture, finished to an even surface. If the plaster is not of sufficient strength, it is likely to fracture beneath the VINOPLAST in the event of heavy impact. <ol style="list-style-type: none"> 1. NEW WORK: Brush down to remove all dirt and loose material. Ensure that surfaces are clean and dry. Priming and sealing: New cement plaster, new fabricated concrete slabs, off-shutter concrete, hard wall or gypsum plaster, etc. Apply one full coat of PROFESSIONAL PLASTER PRIMER (PP 700). (See Patching below). N.B. It is essential that the substrate is completely sealed to avoid formation of bubbles when VINOPLAST is applied. On extremely porous surfaces it may therefore be necessary to apply a first coat of BONDING LIQUID (CVI 14). 2. PREVIOUSLY PAINTED SURFACES: First check whether the plaster under the old paint is sound. <ol style="list-style-type: none"> 2.1 Old pva paint Remove loose and flaking paint, sandpaper thoroughly with medium sandpaper, wash with a solution of POLYCELL SUGAR SOAPPOWDER CLEANER, rinse and allow to dry. Prime all bare spots and cracks with PROFESSIONAL PLASTER PRIMER (PP 700). Make good defective areas. (See Patching below). 2.2 Old gloss paint Remove loose and flaking paint, as above, and sand thoroughly to provide a key for subsequent coats. Prime all bare spots and cracks with PROFESSIONAL PLASTER PRIMER (PP 700). Make good defective areas. (See Patching below). Apply one overall coat of PROFESSIONAL UNIVERSAL UNDERCOAT (PU 1000). Allow to dry thoroughly. (In cold wet conditions some undercoats could take up to 48 hours to dry completely). 2.3 Previously distempered and limewashed surfaces Remove all distemper and limewash completely and apply one coat of BONDING LIQUID (CVI 14). Allow a minimum of 24 hours drying. Make good defective surfaces. (See Patching below). 3. PATCHING: Make good cracks and defects with POLYCELL MENDALL 90 ALL PURPOSE ADHESIVE FILLER smoothed well whilst still wet and allow to dry. Spot prime all filled areas with PLASTER PRIMER (PP 700). |
|----------------------------|---|

| | |
|--------------------|--|
| Application | <p>FINISHING COATS: Basecoat - roller application Thin VINOPLAST with VINOPLAST REDUCER (ABV 901). The amount used will depend entirely on the texture desired, i.e. from a sharp pointed pattern to a smooth rounded pimple pattern. Do not over reduce. Apply one or two liberal even coats of VINOPLAST with either a medium pile synthetic roller or texture roller to achieve complete obliteration.</p> <p>Spatter application If necessary, thin with minimum amount of water to achieve the desired effect. DO NOT OVER THIN. Spatter from a pressurised container equipped with an agitator. Using a spatter gun and depending on the desired effects (spots, twigs, etc.), the pot pressure could vary from between 138 - 310 kPa (20 - 45 psi). These effects are obtained by adjusting the consistency, restricting the degree of atomisation and / or fitting different spatter gun nozzles.</p> <p>HINTS: Spatter effects and larger spots require least atomisation. Thick paint (high consistency) produces a coarse texture. Test spray equipment and pressure settings on an experimental surface until the desired effect is obtained.</p> |
|--------------------|--|

| | |
|-----------------|---|
| Cautions | <ul style="list-style-type: none"> • Avoid painting during inclement weather or if temperature is below 5 °C. • Note thinning instructions. • To ensure that colours on a project are consistent, check that batch numbers correspond. |
|-----------------|---|

| | |
|---------------------------|--|
| Safety Precautions | <ul style="list-style-type: none"> • Keep out of reach of children. • Ensure good ventilation during application and drying. • In case of skin contact, wash with soap and water or a recognised skin cleaner. Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist. If ingested give plenty of water / milk. Do not induce vomiting. Seek medical attention. • Refer to Material Safety Data Sheet for complete information. |
|---------------------------|--|

DISCLAIMER:
The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.
N.B.: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.
BARLOWORLD PLASCON SOUTH AFRICA (PTY) LIMITED

| | | | |
|--|---|---|---|
| <p>CAPE TOWN: P O Box 42 Eppindust 7475 Tel: (021) 505-2400 Fax: (021) 534-3791</p> | <p>DURBAN: Private Bag X16 Mobeni 4060 Tel: (031) 451-3200 Fax: (031) 451-3411</p> | <p>MOGALE CITY (KRUGERSDORP): Private Bag X4010 Kenmare 1745 Tel: (011) 951-4500 Fax: (011) 955-4136</p> | <p>PORT ELIZABETH: P O Box 1594 Port Elizabeth 6000 Tel: (041) 401-1400 Fax: (041) 434-606</p> |
|--|---|---|---|